



Rechargeable Sealed Lead-Acid Battery

PS-12700

12 Volt 70 Amp. Hrs.



Features:

- Absorbent Glass Mat (AGM) technology for superior performance.
- Valve regulated, spill-proof construction.
- Power/volume ratio yielding unrivaled energy density.
- Rugged ABS plastic case and cover
- Approved for transport by air. D.O.T., I.A.T.A., F.A.A. and C.A.B. certified.
- U.L. recognized under file number MH 14328.




PERFORMANCE SPECIFICATIONS


Nominal Voltage	12 volts (6 cells in series)
Nominal Capacity	
20 hour rate (3.50A to 10.50 volts)	70.0 A.H.
10 hour rate (6.40A to 10.50 volts)	64.0 A.H.
5 hour rate (11.40A to 10.20 volts)	57.0 A.H.
1 hour rate (41.00A to 09.00 volts)	41.0 A.H.
Approximate Weight	52.5 pounds (23.8 kg)
Energy Density (20 hour rate)	1.36 Watt-hours/cubic inch (83.1 Watt-hours/l)
Specific Energy (20 hour rate)	16.0 Watt-hours/pound (35.3 Watt-hours/kg)
Internal Resistance (Fully Charged Battery)	5.0 milliohms (approximately)
Maximum Discharge Current (≤ 7 Min.)	210 amperes
Maximum Short-Duration Discharge Current (≤ 10 Sec.)	650 amperes
Terminal Options	Heavy duty post with nut & bolt fasteners
Vibration Test (2000 cycles/minute, 0.10 inch excursion, 2 hours)	No loss in capacity or performance
Shelf Life — % of nominal capacity at 68° F (20° C)	
1 Month.....	97%
3 Months.....	91%
6 Months.....	83%
Operating Temperature Range	
Charge	-4°F (-20°C) to 122°F (50°C)
Discharge	-4°F (-20°C) to 140°F (60°C)
Case	ABS Plastic

CONSTANT POWER DISCHARGE RATINGS							
MODEL	FINAL VOLTAGE	WATTS PER CELL @ 25° C					
		5 MIN	10 MIN	15 MIN	20 MIN	30 MIN	60 MIN
PS-12700	1.75	462	312	238	195	145	84
	1.70	473	319	243	198	148	85
	1.67	478	325	246	201	150	86


Discharge Characteristics



Shelf Life and Storage



Discharge Time vs. Discharge Current




CHARGING

Cycle Applications: Limit initial current to 17.5A. Charge until battery voltage (under charge) reaches 14.40 to 14.70 volts at 68°F (20°C). Hold at 14.40 to 14.70 volts until current drops to approximately 700mA. **“Float” or “Stand-By” Service:** Hold battery across constant voltage source of 13.50 to 13.80 volts continuously.

NOTE: Due to the self-discharge characteristics of this type of battery, it is imperative that they be charged after 6-9 months of storage, otherwise permanent loss of capacity might occur as a result of sulfation.

Physical Dimensions: in. (mm)



All data subject to change without notice.

Tolerances are +/- 0.04 in. (+/- 1mm) and +/- 0.08 in. (+/- 2mm) for height dimensions.



SALES & MARKETING
 3106 Spring Street
 Redwood City, CA 94063 USA
 Tel: 650-364-5001 Fax: 650-366-3662
 national-sales@power-sonic.com



www.power-sonic.com

ISO9002
 FM39170

CUSTOMER SERVICE
 9163 Siempre Viva Road
 San Diego, CA 92154 USA
 Tel: 619-661-2030 Fax: 619-661-3648
 battery@power-sonic.com